



Ti-Pure™

R-741 Titanium Dioxide

Product Information

Slurry Properties

Table 1 summarizes the slurry-handling properties of Ti-Pure™ R-741.

Table 1.

Analysis and Physical Properties of Ti-Pure™ R-741

Property	Ti-Pure™ R-741
Solids, wt%	64.5
Grit-Unbrushed, wt% 325 Mesh	0.035 max.
Grit-Brushed, wt% 325 Mesh	0.020 max.
Slurry Density, lb/gal	15.6
Pigment, lb/gal	10.1
pH	8.1
pa Viscosity, Brookfield at 100 rpm (cP)	150
Tint Strength	100
Biocide, Nonmercuric, Nonformaldehyde Releasing	Yes

Note: All values are typical unless otherwise specified.

Product Description

Ti-Pure™ R-741 is manufactured by slurring Ti-Pure™ R-931 with water and dispersants under conditions that optimize the paint performance of the pigment in the architectural coating.

For safety information, please visit the product Safety Data Sheet (SDS).

Shipping Containers

Ti-Pure™ R-741 is available in rail cars and tank trucks.

CAUTION: Do not use or resell Chemours™ materials in medical applications involving implantation in the human body or contact with internal body fluids or tissues unless agreed to by Seller in a written agreement covering such use. For further information, please contact your Chemours representative. These products may not be directly added to food, pharmaceuticals, cosmetics, or cigarette papers/filters for tobacco products.

For medical emergencies, spills, or other critical situations, call (844) 773-2436 within the United States. For those outside of the United States, call (302) 773-1000. The information set forth herein is furnished free of charge and based on technical data that Chemours believes to be reliable. It is intended for use by persons having technical skill, at their own discretion and risk. The handling precaution information contained herein is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Because conditions of product use are outside our control, Chemours makes no warranties, express or implied, and assumes no liability in connection with any use of this information. As with any material, evaluation of any compound under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents.

NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF CHEMOURS.

For more information, visit tipure.com

© 2020 The Chemours Company FC, LLC. Ti-Pure™ and any associated logos are trademarks or copyrights of The Chemours Company FC, LLC.
Chemours™ and the Chemours Logo are trademarks of The Chemours Company.

C-10414-1 (2/20)